STANDARD FLY ASH CERTIFICATE



FINAL

Prior Reports: None

Certificate Number: CERT221046 Issued: 23 March 2022 Flyash Australia Pty Ltd ABN 68 002 840 271 P.O. Box 190 Eastwood NSW 2122 Email: contact@flyash.com.au www.flyashaustralia.com.au

Product being certified: Product sample date: Sample Identification: Source Power Station: Sample Condition: Certifying Laboratory: Mt Piper Monthly Grab Fly Ash 01-Mar-2022 Sample Code: 22030130 Mount Piper Power Station Tested as Received. Testing Commenced on 04-Mar-2022 Cement Australia - Darra Laboratory, 18 Station Avenue, Darra Queensland 4076 Australia.

Test Results

Test	Moisture	Fineness @ 45 micron	Loss on Ignition	Sulfuric Anhydride	Available Alkali	Chloride Ion	Chemical Composition
	%	% Passed	%	%	%	%	%
Result	0.1	84	1.1	0.1	n/a	< 0.002	94.7
Test Method	AS3583.2	AS3583.1	AS3583.3	AS2350.2	AS3583.12	AS3583.13	AS2350.2
AS 3582.1	0.5 % Maximum	75% Minimum	4.0 % Maximum	3.0 % Maximum	-	0.1 % Maximum	70% Minimum

Test	Relative Density	Relative Water Requirement	Strength Index 7 Day Acc.	Reference Cement Details	
		%	%	Identification:: 22030214	
Result	2.12	97	96	Source: Goliath GP	
Test Method	AS3583.5	AS3583.6	AS3583.6	Product Type: Type GP	
AS 3582.1	-	-	75% Minimum	Sample Date: 08-Mar-22	

Additional Testing - Oxides

					-		
Test	CaO by XRF	SiO ₂ by XRF	Al ₂ O ₃ by XRF	Fe ₂ O ₃ by XRF	SO ₃ by XRF	MgO by XRF	Na ₂ O by XRF
	%	%	%	%	%	%	%
Result	0.3	67.9	24.1	2.7	0.1	0.2	0.41
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

Test	K₂O by XRF	SrO by XRF	TiO2 by XRF	P ₂ O ₅ by XRF	Mn ₂ O ₃ by XRF	Total Alkali (NaEQ)
	%	%	%	%	%	%
Result	2.40	<0.1	0.9	0.2	< 0.1	1.99
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

This sample grade conforms to the following requirements of AS 3582.1:2016

Special Grade 1 Grade 2 X



Signatory - Cement Australia Chemical Testing Construction Materials Testing

Notes:

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Cement Australia - Darra Laboratory NATA Accredited Laboratory Numbers 187 188



This test report shall not be reproduced except in full, without written approval from Flyash Australia.