STANDARD FLY ASH CERTIFICATE



FINAL
Prior Reports: None

Certificate Number: CERT202701

Issued: 30 November 2020

Product being certified: Mundra Monthly Grab Fly Ash Product sample date: 05-Nov-2020

Sample Identification: Sample Code: 20110361

Source Power Station: Imported Ash

Sample Condition: Tested as Received. Testing Commenced on 10-Nov-2020

Certifying Laboratory: Cement Australia - Darra Laboratory,

18 Station Avenue, Darra Queensland 4076 Australia.

Head Office C/- Lindfield Corporate Centre Suite 18, 12 Tryon Road Lindfield NSW 2070

Flyash Australia Pty Ltd

ABN 68 002 840 271

Tel: (02) 9413 8422 Fax: (02) 9413 84.32 www.flyashaustralia.com.au

Test Results

Test	Moisture	Fineness @ 45 micron	Loss on Ignition	Sulfuric Anhydride	Available Alkali	Chloride Ion	Chemical Composition
	%	% Passed	%	%	%	%	%
Result	0.1	83	0.2	1.0	n/a	0.002	76.5
Test Method	AS3583.2	AS3583.1	AS3583.3	AS2350.2	AS3583.12	AS3583.13	AS2350.2
AS 3582.1	0.5 % Maximum	75% Minimum	4.0 % Maximum	3.0 % Maximum	-	0.1 % Maximum	70% Minimum

Test	Relative Density	Relative Water Requirement	Strength Index 7 Day Acc.	Reference Cement Details	
		%	%	Identification:: 20110301	
Result	2.70	91	121	Source: Goliath GP	
Test Method	AS3583.5	AS3583.6	AS3583.6	Product Type: Type GP	
AS 3582.1	-	-	75% Minimum	Sample Date: 10-Nov-20	

Additional Testing - Oxides

Test	CaO by XRF %	SiO ₂ by XRF %	Al ₂ O ₃ by XRF %	Fe ₂ O ₃ by XRF %	SO ₃ by XRF	MgO by XRF %	Na ₂ O by XRF %
Result	12.0	44.6	20.8	11.1	1.0	6.8	1.20
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

Test	K₂O by XRF	SrO by XRF	TiO2 by XRF	P ₂ O ₅ by XRF	Mn ₂ O ₃ by XRF	Total Alkali (NaEQ)
	%	%	%	%	%	%
Result	1.03	<0.1	0.8	0.3	0.1	1.88
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

This sample grade conforms to the following requirements of AS 3582.1:2016

Special	Grade 1	Grade 2
	Х	

Approved Signatory

A Prem Signatory - Cement Australia Chemical Testing

Construction Materials Testing

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Cement Australia - Darra Laboratory NATA Accredited Laboratory Numbers 187 188







Notes: