STANDARD FLY ASH CERTIFICATE



FINAL

Prior Reports: None

Certificate Number: CERT211877 Issued: 20 July 2021 Flyash Australia Pty Ltd ABN 68 002 840 271 P.O. Box 190 Eastwood NSW 2122 Email: contact@flyash.com.au www.flyashaustralia.com.au

Product being certified: Product sample date: Sample Identification: Source Power Station: Sample Condition: Certifying Laboratory: Mt Piper Monthly Grab Fly Ash 06-Jul-2021 Sample Code: 21070120 Mount Piper Power Station Tested as Received. Testing Commenced on 06-Jul-2021 Cement Australia - Darra Laboratory, 18 Station Avenue, Darra Queensland 4076 Australia.

Test Results

Test	Moisture	Fineness @ 45 micron	Loss on Ignition	Sulfuric Anhydride	Available Alkali	Chloride Ion	Chemical Composition
	%	% Passed	%	%	%	%	%
Result	< 0.1	84	2.2	< 0.1	n/a	< 0.001	93.3
Test Method	AS3583.2	AS3583.1	AS3583.3	AS2350.2	AS3583.12	AS3583.13	AS2350.2
AS 3582.1	0.5 % Maximum	75% Minimum	4.0 % Maximum	3.0 % Maximum	-	0.1 % Maximum	70% Minimum

Test	Relative Density	Relative Water Requirement	Strength Index 7 Day Acc.	Reference Cement Details
		%	%	Identification:: 21070202
Result	2.15	96	102	Source: Goliath GP
Test Method	AS3583.5	AS3583.6	AS3583.6	Product Type: Type GP
AS 3582.1	-	-	75% Minimum	Sample Date: 08-Jul-21

Additional Testing - Oxides

Test	CaO by XRF	SiO ₂ by XRF	Al ₂ O ₃ by XRF	Fe ₂ O ₃ by XRF	SO ₃ by XRF	MgO by XRF	Na ₂ O by XRF
	%	%	%	%	%	%	%
Result	0.2	66.6	24.3	2.4	< 0.1	0.2	0.48
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

Test	K₂O by XRF	SrO by XRF	TiO2 by XRF	P₂O₅ by XRF	Mn ₂ O ₃ by XRF	Total Alkali (NaEQ)
	%	%	%	%	%	%
Result	2.59	<0.1	0.9	0.3	< 0.1	2.18
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

This sample grade conforms to the following requirements of AS 3582.1:2016

Special Grade 1 Grade 2 X



Signatory - Cement Australia Chemical Testing Construction Materials Testing

Notes:

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Cement Australia - Darra Laboratory NATA Accredited Laboratory Numbers 187 188

