STANDARD FLY ASH CERTIFICATE



FINAL
Prior Reports: None

Certificate Number: CERT213564

Issued: 29 November 2021

Flyash Australia Pty Ltd
ABN 68 002 840 271
P.O. Box 190
Eastwood NSW 2122
Email: contact@flyash.com.au
www.flyashaustralia.com.au

Product being certified: Mt Piper Monthly Grab Fly Ash

Product sample date: 08-Nov-2021

Sample Identification: Sample Code: 21110244
Source Power Station: Mount Piper Power Station

Sample Condition: Tested as Received. Testing Commenced on 08-Nov-2021

Certifying Laboratory: Cement Australia - Darra Laboratory,

18 Station Avenue, Darra Queensland 4076 Australia.

Test Results

Test	Moisture	Fineness @ 45 micron	Loss on Ignition	Sulfuric Anhydride	Available Alkali	Chloride Ion	Chemical Composition
	%	% Passed	%	%	%	%	%
Result	< 0.1	84	1.8	< 0.1	n/a	< 0.002	93.9
Test Method	AS3583.2	AS3583.1	AS3583.3	AS2350.2	AS3583.12	AS3583.13	AS2350.2
AS 3582.1	0.5 % Maximum	75% Minimum	4.0 % Maximum	3.0 % Maximum	-	0.1 % Maximum	70% Minimum

Test	Relative Density	Relative Water Requirement	Strength Index 7 Day Acc.	Reference Cement Details	
		%	%	Identification:: 21110278	
Result	2.13	95	93	Source: Goliath GP	
Test Method	AS3583.5	AS3583.6	AS3583.6	Product Type: Type GP	
AS 3582.1	-	-	75% Minimum	Sample Date: 08-Nov-21	

Additional Testing - Oxides

Test	CaO by XRF %	SiO ₂ by XRF %	Al ₂ O ₃ by XRF %	Fe ₂ O ₃ by XRF %	SO ₃ by XRF	MgO by XRF %	Na ₂ O by XRF %
Result	0.2	67.0	24.3	2.6	< 0.1	0.2	0.56
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

Test	K₂O by XRF	SrO by XRF	TiO2 by XRF	P ₂ O ₅ by XRF	Mn₂O₃ by XRF	Total Alkali (NaEQ)
	%	%	%	%	%	%
Result	2.46	<0.1	0.8	0.3	< 0.1	2.18
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

This sample grade conforms to the following requirements of AS 3582.1:2016

Special	Grade 1	Grade 2
	Х	

Approved Signatory

A Prem Signatory - Cement Australia Chemical Testing

Construction Materials Testing

Notes:

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Cement Australia - Darra Laboratory NATA Accredited Laboratory Numbers 187 188



