STANDARD FLY ASH CERTIFICATE



FINAL

Prior Reports: None

Certificate Number: CERT213565 Issued: 29 November 2021 Flyash Australia Pty Ltd ABN 68 002 840 271 P.O. Box 190 Eastwood NSW 2122 Email: contact@flyash.com.au www.flyashaustralia.com.au

Product being certified: Product sample date: Sample Identification: Source Power Station: Sample Condition: Certifying Laboratory: Eraring Monthly Grab Fly Ash 10-Nov-2021 Sample Code: 21110523 Eraring Power Station Tested as Received. Testing Commenced on 12-Nov-2021 Cement Australia - Darra Laboratory, 18 Station Avenue, Darra Queensland 4076 Australia.

Test Results

Test	Moisture	Fineness @ 45 micron	Loss on Ignition	Sulfuric Anhydride	Available Alkali	Chloride Ion	Chemical Composition
	%	% Passed	%	%	%	%	%
Result	0.1	86	1.2	0.1	n/a	< 0.002	93.8
Test Method	AS3583.2	AS3583.1	AS3583.3	AS2350.2	AS3583.12	AS3583.13	AS2350.2
AS 3582.1	0.5 % Maximum	75% Minimum	4.0 % Maximum	3.0 % Maximum	-	0.1 % Maximum	70% Minimum

Test	Relative Density	Relative Water Requirement	Strength Index 7 Day Acc.	Reference Cement Details	
		%	%	Identification:: 21110823	
Result	2.13	95	95	Source: Goliath GP	
Test Method	AS3583.5	AS3583.6	AS3583.6	Product Type: Type GP	
AS 3582.1	-	-	75% Minimum	Sample Date: 19-Nov-21	

Additional Testing - Oxides

Test	CaO by XRF	SiO ₂ by XRF	Al ₂ O ₃ by XRF	Fe ₂ O ₃ by XRF	SO ₃ by XRF	MgO by XRF	Na ₂ O by XRF
	%	%	%	%	%	%	%
Result	1.5	66.0	24.0	3.8	0.1	0.6	0.54
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

Test	K₂O by XRF	SrO by XRF	TiO2 by XRF	P₂O₅ by XRF	Mn ₂ O ₃ by XRF	Total Alkali (NaEQ)
	%	%	%	%	%	%
Result	1.38	<0.1	1.0	0.2	< 0.1	1.45
Test Method	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2	AS2350.2

This sample grade conforms to the following requirements of AS 3582.1:2016

Special Grade 1 Grade 2 X



Signatory - Cement Australia Chemical Testing Construction Materials Testing

Notes:

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Cement Australia - Darra Laboratory NATA Accredited Laboratory Numbers 187 188

